





LAB N° 0143 L

 To FIDIVI Tessitura Vergnano spa  
 Regione Masio, 19 bis  
 10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test report N° S.10149	Test N° 23.10898	date 09-06-2023	Pag. 1/1
<u>Sample identification</u>		Date of arrival 23-05-2023	Sample id 23.00227.01	Sample reference		
Article : DREAM						
Test	ABRASION					
Form and terms						
Test method : UNI EN ISO 12947-1:2000+EC 1-2010+UNI EN ISO 12947-2:2017. Determination of the abrasion resistance of fabrics by the Martindale method. Determination of specimen breakdown						
Apparatus : MARTINDALE						
Material : Standard Abradent Fabric SM 25						
Load : 12Kpa (nominal pressure)						
Felt : Woven felt						
Pilling : The possible pilling created during the test is cut						
<u>Test results</u>	Test start 30-05-2023	Test end 09-06-2023	Notes			
BREAKING POINT :100000 revs						
Sample 1 :100000 revs						
Sample 2 :100000 revs						
Sample 3 :100000 revs						
Measure uncertainty extended:			Signatures			
			The Textile Laboratory Manager		CEO	
			 (Dr. Jessica Fabbro)		 (Eng. Alberto Canova)	
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its integrity, unless approved in writing by BQT laboratory.</small>						