

TEST REPORT N° 16/24557

page 1 out of 2

Mod.018 Rev. 2 del 12.10.2015

WEB Request Number	
Receipt Number	16/23923
Receipt date	01/07/16
Test beginning date	01/07/16
Test end date	05/07/16
Document issued on	11/07/16

FIDIVI TESSITURA VERGNANO S.p.A.

Regione Masio, 19 bis
10046 POIRINO (TO)
Phone +39 (011) 9430662
Fax +39 (011) 9461820



SAMPLE IDENTIFICATION:

A TESSUTO ART. ALBA

THIS DOCUMENT CONTAINS THE FOLLOWING TESTS:

Code	Test	Test Method
CS0310	Color fastness to rubbing	UNI EN ISO 105-X12:2003

Tests results refer only to tested samples.
On each page there is the Institute dry stamp.
Tested samples are available for 3 months.

The Analysts	Technical Manager
Prof. Andrea Franchi - Prof. Paolo Borgiotti 	Prof. Giuseppe Bartolini 

Private document. It is not allowed to publish and spread it without lab's written authorization.

TEST REPORT N° 16/24557

page 2 out of 2

Mod.018 Rev. 2 del 12.10.2015

Beginning of Test Report

CS0310	Color fastness to rubbing
<i>Test methods</i>	UNI EN ISO 105-X12:2003

Rev.1.0 -25/03/2016

Testing date 05/07/2016

Test Results :

<i>Sample identification</i>	TESSUTO ART. ALBA	
	<i>Staining index</i>	
	<i>Warp</i>	<i>Weft</i>
<i>Dry rubbing</i>	4/5	4/5
<i>Wet rubbing</i>	5	5

Nota: for plain fabric, test is performed with circular finger; for raised fabric, test is performed with rectangular finger

NB. The results reported in the tables above refer to a test analysis of the samples submitted.

End of Test Report.