





LAB N° 0143 L

 To FIDIVI Tessitura Vergnano spa
 Regione Masio, 19 bis
 10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N.	date	Pag.
			5117	23/03/2022	1/1
<u>Sample identification</u>	Date of arrival	Sample id	Sample reference		
Article : BONDAI	21/03/2022	22.00110.10			
Test	COLOUR FASTNESS TO WET RUBBING				
Form and terms					
Test method	: UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing				
Apparatus	: CROCKMETER				
N.of rubs	: 10				
Material	: Wet cotton cloths				
Load	: 9 N				
Conditioning	: Minimum 4 hours at 20+/-2°C and R.H.65+/-4%				
Environment of testing	: 20+/-2°C and R.H.65+/-4%				
<u>Test results</u>	Test start	Test end	Notes		
	23/03/2022	23/03/2022			
Staining Longitudinal	:4/5	index			
Staining Transversal	:4/5	index			
Measure uncertainty extended:			Signatures		
			The Textile Laboratory Manager  (Dr. Jessica Fabbro)		
			CEO  (Eng. Alberto Canova)		

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.

END OF TEST REPORT



Biella Qualità Totale srl



LAB N° 0143 L

 To FIDIVI Tessitura Vergnano spa
 Regione Masio, 19 bis
 10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N. 5118	date 23/03/2022	Pag. 1/1
<u>Sample identification</u>	Date of arrival 21/03/2022	Sample id 22.00110.10	Sample reference		
Article : BONDAI					
Test	COLOUR FASTNESS TO DRY RUBBING				
Form and terms					
Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing					
Apparatus : CROCKMETER					
N.of rubs : 10					
Material : Dry cotton cloths					
Load : 9 N					
Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4%					
Environment of testing : 20+/-2°C and R.H.65+/-4%					
<u>Test results</u>	Test start 23/03/2022	Test end 23/03/2022	Notes		
Staining Longitudinal	:4/5	index			
Staining Transversal	:4/5	index			
Measure uncertainty extended:			Signatures		
			The Textile Laboratory Manager  (Dr. Jessica Fabbro)		
			CEO  (Eng. Alberto Canova)		
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.</small>					

END OF TEST REPORT

Biella Qualità Totale srl