





LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa  
Regione Masio, 19 bis  
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N. 8602	date 23/05/2022	Pag. 1/1
<u>Sample identification</u>	Date of arrival 09/05/2022	Sample id 22.00177.01	Sample reference		
Article : BRAVO					
Test	COLOUR FASTNESS TO LIGHT				
Form and terms					
Test method	: UNI EN ISO 105-B02:2014 Method 1 Textiles. Tests for colour fastness. Colour fastness to artificial light: Xenon arc fading lamp				
Apparatus	: XENOTEST Q-SUN Xe2				
Assessment	: Blue scale				
Condition	: Normal				
Type of exposition	: Continuos				
Humidity	: 40%				
<u>Test results</u>	Test start 11/05/2022	Test end 23/05/2022	Notes		
Fastness index	:6				
Measure uncertainty extended:			Signatures		
		The Textile Laboratory Manager		CEO	
		 (Dr. Jessica Fabbro)		 (Eng. Alberto Canova)	
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its intirety, unless approved in writing by BQT laboratory.</small>					