

**TEST REPORT N° 19/18174 - SUPPLEMENT**  
**Replacement of test report n. 19/17381**

**page 1 out of 2**

Mod.018 Rev. 2 del 12.10.2015

<b>WEB Request Number</b>	
<b>Receipt Number</b>	<b>19/16973</b>
<b>Receipt date</b>	<b>28/03/19</b>
<b>Test beginning date</b>	
<b>Test end date</b>	<b>02/04/19</b>
<b>Document issued on</b>	<b>05/04/19</b>

**FIDIVI TESSITURA VERGNANO S.p.A.**

**Regione Masio, 19 bis**  
**10046 POIRINO (TO)**  
**Phone +39 (011) 9430662**  
**Fax +39 (011) 9461820**



**SAMPLE IDENTIFICATION:**

**A TESSUTO ART. CORTE**

**THIS DOCUMENT CONTAINS THE FOLLOWING TESTS:**

<b>Code</b>	<b>Test</b>	<b>Test Method</b>
CS0310	Color fastness to rubbing	UNI EN ISO 105-X12:2016

Tests results refer only to tested samples submitted by the customer.  
On each page there is the Institute dry stamp.  
Tested samples are available for 3 months.

<p><b>The Analysts</b></p>  <p>Prof. Andrea Franchi</p>	<p><b>Technical Manager</b></p>  <p>Prof. Giuseppe Bartolini</p>
--	--

Private document. It is not allowed to publish and spread it without lab's written authorization.

**TEST REPORT N° 19/18174 - SUPPLEMENT**  
**Replacement of test report n. 19/17381**

**page 2 out of 2**

Mod.018 Rev. 2 del 12.10.2015

Beginning of Test Report

CS0310 Color fastness to rubbing

Test methods **UNI EN ISO 105-X12:2016**

Rev.1.0 -25/03/2016

Testing date 02/04/2019

**Test Results :**

Sample identification	<b>TESSUTO ART. CORTE</b>	
	<i>Staining index</i>	
	<i>Warp</i>	<i>Weft</i>
Dry rubbing	<b>4/5</b>	<b>4/5</b>
Wet rubbing	<b>4/5</b>	<b>4/5</b>

*Nota: for plain fabric, test is performed with circular finger; for raised fabric, test is performed with rectangular finger*

*NB. The results reported in the tables above refer to a test analysis of the samples submitted.*

End of Test Report.