



To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)



00130

TEST REPORT			Test report N° S.15154	Test N° 25.18557	date 01-10-2025	Pag. 1/1
<u>Sample identification</u>	Date of arrival 10-09-2025	Sample id 25.00359.04	Sample reference			
Article : DELIA						
Test	COLOUR FASTNESS TO LIGHT					
Form and terms Test method : UNI EN ISO 105-B02:2014 Method 1 Textiles. Tests for colour fastness. Colour fastness to artificial light: Xenon arc fading lamp Apparatus : XENOTEST Q-SUN Xe2 Assessment : Blue scale Condition : Normal Type of exposition : Continuos Humidity : 40% Exposure cycle : A1 Rating (with blue scale 1-8): 1: Maximum change ; 8: No change						
<u>Test results</u>	Test start 10-09-2025	Test end 30-09-2025	Notes			
Fastness index :6						
Measure uncertainty extended:			Signatures The Textile Laboratory Manager  <i>(Dr. Jessica Fabbro)</i> CEO  <i>(Eng. Alberto Canova)</i>			

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its intirety, unless approved in writing by BQT laboratory.