



00130


To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

TEST REPORT			Test report N° S.14035	Test N° 25.17218	date 16-09-2025	Pag. 1/1
<u>Sample identification</u>		Date of arrival 10-09-2025	Sample id 25.00359.04	Sample reference		
Article : DELIA						
Test	COLOUR FASTNESS TO DRY RUBBING					
Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER Number of rubs : 10 Material : Fabric versus dry cotton rubbing cloth Load applied : (9 +/- 0.2) N Conditioning : Minimum 4 hours at (20 +/- 2)°C and (65 +/- 4)% R.H. Environment of testing : (20 +/- 2)°C and (65 +/- 4)% R.H. Rubbing finger : Cylindrical of (16 +/- 0.1) mm diameter Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain						
<u>Test results</u>	Test start 16-09-2025	Test end 16-09-2025	Notes			
Staining Longitudinal :4/5 index Staining Transversal :4/5 index						
Measure uncertainty extended:			Signatures The Textile Laboratory Manager (Dr. Jessica Fabbro) CEO (Eng. Alberto Canova)			
Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its integrity, unless approved in writing by BQT laboratory.						

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)



00130

TEST REPORT			Test report N° S.14036	Test N° 25.17219	date 16-09-2025	Pag. 1/1				
<u>Sample identification</u>	Date of arrival 10-09-2025	Sample id 25.00359.04	Sample reference							
Article : DELIA										
<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 15%; padding: 5px;">Test</td> <td style="padding: 5px; text-align: center;">COLOUR FASTNESS TO WET RUBBING</td> </tr> <tr> <td colspan="2" style="padding: 5px;"> Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER Number of rubs : 10 Material : Fabric versus wet cotton rubbing cloth Load applied : (9 +/- 0.2) N Conditioning : Minimum 4 hours at (20 +/- 2)°C and (65 +/- 4)% R.H. Environment of testing : (20 +/- 2)°C and (65 +/- 4)% R.H. Rubbing finger : Cylindrical of (16 +/- 0.1) mm diameter Percentage of soak : From 95% to 100% of Grade 3 Water (UNI EN ISO 3696:1996) Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain </td> </tr> </table>							Test	COLOUR FASTNESS TO WET RUBBING	Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER Number of rubs : 10 Material : Fabric versus wet cotton rubbing cloth Load applied : (9 +/- 0.2) N Conditioning : Minimum 4 hours at (20 +/- 2)°C and (65 +/- 4)% R.H. Environment of testing : (20 +/- 2)°C and (65 +/- 4)% R.H. Rubbing finger : Cylindrical of (16 +/- 0.1) mm diameter Percentage of soak : From 95% to 100% of Grade 3 Water (UNI EN ISO 3696:1996) Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain	
Test	COLOUR FASTNESS TO WET RUBBING									
Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER Number of rubs : 10 Material : Fabric versus wet cotton rubbing cloth Load applied : (9 +/- 0.2) N Conditioning : Minimum 4 hours at (20 +/- 2)°C and (65 +/- 4)% R.H. Environment of testing : (20 +/- 2)°C and (65 +/- 4)% R.H. Rubbing finger : Cylindrical of (16 +/- 0.1) mm diameter Percentage of soak : From 95% to 100% of Grade 3 Water (UNI EN ISO 3696:1996) Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain										
<u>Test results</u>	Test start 16-09-2025	Test end 16-09-2025	Notes							
Staining Longitudinal :4/5 index Staining Transversal :4/5 index										
Measure uncertainty extended:			Signatures The Textile Laboratory Manager  (Dr. Jessica Fabbro) CEO  (Eng. Alberto Canova)							

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its integrity, unless approved in writing by BQT laboratory.