

FIDIVI*	CARATTERISTICHE PRINCIPALI - PRINCIPAL CHARACTERISTICS CARACTERISTIQUES PRINCIPALES - HAUPT EIGENSCHAFTEN	Date 16/04/2024 Edition 00
----------------	--	-------------------------------

Caratteristica Characteristic Caractéristique Charakterdarsteller	Norma Norm Norme Norm	Tolleranza Tolerance Tolérance Toleranz	Dichiarato Declared Déclaré Deklariert		
Peso (g/ml) – Weight (g/lm) Poids (g/ml) - Gewicht (g/lm)	EN 12127	± 5 %	420		
Peso (g/m²) - Weight (g/m²) Poids (g/m²) - Gewicht (g/m²)	EN 12127	± 5 %	300		
Altezza (cm) - Width (cm) Largeur (cm) - Breite (cm)	-----	± 2 %	140		
Resistenza all'abrasione (cicli) Abrasion resistance (rubs) Résistance à l'abrasion (tours) Scheuerfestigkeit (Scheuertouren)	ISO 12947-2 (Martindale)	± 10 %	100.000		
Solidità del colore alla luce (scala dei blu) Light fastness (blue scale) Solidité à la lumière (échelle des bleu) Lichtechtheit (Blaumaßstabe)	ISO 105-B02 (Xenotest)	da 5 a 8	6		
Solidità del colore allo sfregamento (scala dei grigi) Fastness to rubbing (grey scale) Solidité au frottement (échelle des gris) Reibechtheit (Graumaßstabe)	ISO 105-X12 (Crockmeter)	da 4 a 5	4/5		
Pilling (2000 cicli) - Pilling (2000 rubs) Pilling (2000 tours) - Pilling (2000 scheuertouren)	ISO 12945-2	da 4 a 5	5		
Composizione Composition Composition Zusammensetzung	60% POLIESTERE RICICLATO – 40% POLIESTERE 60% RECYCLED POLYESTER – 40% POLYESTER 60% POLYESTER RECYCLE' – 40% POLYESTER 60% POLYESTER RECYCELT – 40% POLYESTER				
Leggere differenze di colore tra un lotto e l'altro sono da considerarsi normali Slight colour differences between one lot and another have to be considered within commercial tolerance Légères différences de couleur entre un lot et l'autre doivent être considérés comme étant normales Leichte Farbunterschiede sind zwischen zwei Partien als normal zu betrachten					
Reazione al fuoco – Flammability - Classement au feu – Feuersicherung					
Can meet UNI 9175 Class 1 IM EN 1021-1 & 2 BS 5852 CRIB 5 BS 7176 Class Medium Hazard California TB 117-2013	Altri test fuoco possono essere superati, il superamento di alcuni test fuoco può dipendere dalla schiuma utilizzata Will also pass other flammability standards. Flame retardant performance is dependent upon the foam used Autres tests feu peuvent être passés. La performance au feu dépend de la mousse utilisée Wird auch andere Brandschutzstandards erfüllen. Die flammhemmende Leistung ist anhängig von dem verwendeten Schaum				
Manutenzione e lavaggio – Cleaning and washing – Nettoyage et lavage – Reinigung und waschen					
60 P					
Global Recycled Standard © 2016 GRS logo GRS Recycled Polyester Certified by ICEA [ICEA-TX-1136]	GRS RECYCLED FROM BOTTLES	OEKO TEX® STANDARD 100 21CX00147 CENTROCOT www.oeko-tex.com	GUARANTEE 5 YEARS		FIDIVI* USES 100% GREEN ENERGY

DEMETRA