





LAB N° 0143 L

 To FIDIVI Tessitura Vergnano spa  
 Regione Masio, 19 bis  
 10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test report N° S.4025	Test N° 24.04818	date 04-03-2024	Pag. 1/1
<u>Sample identification</u>		Date of arrival 19-02-2024	Sample id 24.00077.05	Sample reference		
Article : DEMETRA						
Test	COLOUR FASTNESS TO LIGHT					
Form and terms						
Test method : UNI EN ISO 105-B02:2014 Method 1 Textiles. Tests for colour fastness. Colour fastness to artificial light: Xenon arc fading lamp						
Apparatus : XENOTEST Q-SUN Xe2						
Assessment : Blue scale						
Condition : Normal						
Type of exposition : Continuos						
Humidity : 40%						
Exposure cycle : A1						
Rating (with blue scale 1-8): 1: Maximum change ; 8: No change						
<u>Test results</u>	Test start 19-02-2024	Test end 04-03-2024	Notes			
Fastness index :6						
Measure uncertainty extended:			Signatures			
			The Textile Laboratory Manager		CEO	
			 (Dr. Jessica Fabbro)		 (Eng. Alberto Canova)	
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its intirety, unless approved in writing by BQT laboratory.</small>						