



To FIDIVI Tessitura Vergnano spa  
 Regione Masio, 19 bis  
 10046 POIRINO (TO)



LAB N° 0143 L

Attn of Sig. M. Fullin

TEST REPORT		Test report N° S.4244	Test N° 24.05069	date 07-03-2024	Pag. 1/1
<u>Sample identification</u>		Date of arrival 19-02-2024	Sample id 24.00077.05	Sample reference	
Article : DEMETRA					
Test	ABRASION				
Form and terms					
Test method	: UNI EN ISO 12947-1:2000+EC 1-2010+UNI EN ISO 12947-2:2017. Determination of the abrasion resistance of fabrics by the Martindale method. Determination of specimen breakdown				
Apparatus	: MARTINDALE				
Material	: Standard Abradent Fabric SM 25				
Load	: 12Kpa (nominal pressure)				
Felt	: Woven felt				
Pilling	: The possible pilling created during the test is cut				
<u>Test results</u>	Test start 26-02-2024	Test end 07-03-2024	Notes		
BREAKING POINT	:100000 revs				
Sample 1	:100000 revs				
Sample 2	:100000 revs				
Sample 3	:100000 revs				
Measure uncertainty extended:	Signatures				
	The Textile Laboratory Manager		CEO		
	 (Dr. Jessica Fabbro)		 (Eng. Alberto Canova)		

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its entirety, unless approved in writing by BQT laboratory.