



LAB N° 0143 L

 To FIDIVI Tessitura Vergnano spa
 Regione Masio, 19 bis
 10046 POIRINO (TO)

Attn of Sig. M. Fullin



TEST REPORT			Test report N° S.9237	Test N° 23.09902	date 24-05-2023	Pag. 1/1
<u>Sample identification</u>	Date of arrival 23-05-2023	Sample id 23.00227.01	Sample reference			
Article : DREAM						
Test	COLOUR FASTNESS TO DRY RUBBING					
Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER N.of rubs : 10 Material : Dry cotton cloths Load : 9 N Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4% Environment of testing : 20+/-2°C and R.H.65+/-4% Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain						
<u>Test results</u>	Test start 24-05-2023	Test end 24-05-2023	Notes			
Staining Longitudinal	:4/5	index				
Staining Transversal	:4/5	index				
Measure uncertainty extended:			Signatures The Textile Laboratory Manager  (Dr. Jessica Fabbro)			
				CEO  (Eng. Alberto Canova)		
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its integrity, unless approved in writing by BQT laboratory.</small>						

To FIDIVI Tessitura Vergnano spa
 Regione Masio, 19 bis
 10046 POIRINO (TO)



LAB N° 0143 L

Attn of Sig. M. Fullin

TEST REPORT			Test report N° S.9238	Test N° 23.09903	date 24-05-2023	Pag. 1/1
<u>Sample identification</u>		Date of arrival 23-05-2023	Sample id 23.00227.01	Sample reference		
Article : DREAM						
Test	COLOUR FASTNESS TO WET RUBBING					
Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER N.of rubs : 10 Material : Wet cotton cloths Load : 9 N Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4% Environment of testing : 20+/-2°C and R.H.65+/-4% Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain						
<u>Test results</u>	Test start 24-05-2023	Test end 24-05-2023	Notes			
Staining Longitudinal	:4/5	index				
Staining Transversal	:4/5	index				
Measure uncertainty extended:			Signatures The Textile Laboratory Manager  (Dr. Jessica Fabbro)			
			CEO  (Eng. Alberto Canova)			
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its intirety, unless approved in writing by BQT laboratory.</small>						