



LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test report N° S.1446	Test N° 24.01800	date 26-01-2024	Pag. 1/1
<u>Sample identification</u>		Date of arrival 18-01-2024	Sample id 24.00025.11	Sample reference		
Article : FIOCCO Compos. : 100% PL						
Test		COLOUR FASTNESS TO WET RUBBING				
Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER N.of rubs : 10 Material : Wet cotton cloths Load : 9 N Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4% Environment of testing : 20+/-2°C and R.H.65+/-4% Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain						
<u>Test results</u>		Test start 26-01-2024	Test end 26-01-2024	Notes		
Staining Longitudinal : 4/5 index Staining Transversal : 4/5 index						
Measure uncertainty extended:				Signatures The Textile Laboratory Manager (Dr. Jessica Fabbro) CEO (Eng. Alberto Canova)		

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its entirety, unless approved in writing by BQT laboratory.



LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test report N° S.1445	Test N° 24.01799	date 26-01-2024	Pag. 1/1
<u>Sample identification</u>		Date of arrival 18-01-2024	Sample id 24.00025.11	Sample reference		
Article : FIOCCO Compos. : 100% PL						
Test	COLOUR FASTNESS TO DRY RUBBING					
Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER N.of rubs : 10 Material : Dry cotton cloths Load : 9 N Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4% Environment of testing : 20+/-2°C and R.H.65+/-4% Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain						
<u>Test results</u>	Test start 26-01-2024	Test end 26-01-2024	Notes			
Staining Longitudinal : 4/5 index Staining Transversal : 4/5 index						
Measure uncertainty extended:			Signatures The Textile Laboratory Manager  (Dr. Jessica Fabbro) CEO  (Eng. Alberto Canova)			

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its integrity, unless approved in writing by BQT laboratory.