

**FIDIVI\***

TESSITURA VERGNANO

**CARATTERISTICHE PRINCIPALI - PRINCIPAL CHARACTERISTICS**  
**CARACTERISTIQUES PRINCIPALES - HAUPT EIGENSCHAFTEN**

Date 16/01/2019  
Edition 03

**IN & OUT**

Caratteristica Characteristic Caractéristique Charakterdarsteller	Norma Norm Norme Norm	Tolleranza Tolerance Tolérance Toleranz	Dichiarato Declared Déclaré Deklariert
Peso (g/ml) - Weight (g/lm) Poids (g/ml) - Gewicht (g/lm)	EN 12127	± 5 %	365
Peso (g/m <sup>2</sup> ) - Weight (g/m <sup>2</sup> ) Poids (g/m <sup>2</sup> ) - Gewicht (g/m <sup>2</sup> )	EN 12127	± 5 %	255
Altezza (cm) - Width (cm) Largeur (cm) - Breite (cm)	-----	± 2 %	140
Resistenza all'abrasione (cicli) Abrasion resistance (rubs) Résistance à l'abrasion (tours) Scheuerfestigkeit (Scheuertouren)	ISO 12947-2 (Martindale)	± 10 %	50000
Solidità del colore alla luce (scala dei blu) Light fastness (blue scale) Solidité à la lumière (échelle des bleu) Lichtechtheit (Blaumaßstabe)	ISO 105-B02 (Xenotest)	da 7 a 8	7/8
Solidità del colore alla luce alle intemperie (scala dei blu) Light fastness severe weather (blue scale) Solidité à la lumière intempéries (échelle des bleu) Lichtechtheit schlechtes wetter (Blaumaßstabe)	ISO 105-B04	da 7 a 8	7/8
Solidità del colore alla luce alle intemperie (scala dei grigi) Light fastness severe weather (grey scale) Solidité à la lumière intempéries (échelle des gris) Lichtechtheit schlechtes wetter (Graumaßstabe)	ISO 105-B04 1000 hours	da 4 a 5	4/5
Solidità del colore allo sfregamento (scala dei grigi) Fastness to rubbing (grey scale) Solidité au frottement (échelle des gris) Reibechtheit (Graumaßstabe)	ISO 105-X12 (Crockmeter wet-dry)	da 4 a 5	4/5
Pilling (2000 cicli) - Pilling (2000 rubs) Pilling (2000 tours) - Pilling (2000 scheuertouren)	ISO 12945-2	da 4 a 5	5
Composizione Composition Composition Zusammensetzung	100% POLIESTERE FR OUTDOOR 100% POLYESTER FR OUTDOOR 100% POLYESTER OUTDOOR 100% POLYESTER OUTDOOR		

Leggere differenze di colore tra un lotto e l'altro sono da considerarsi normali

Slight colour differences between one lot and another have to be considered within commercial tolerance

Légères différences de couleur entre un lot et l'autre doivent être considérés comme étant normales

Leichte Farbunterschiede sind zwischen zwei Partien als normal zu betrachten

**Reazione al fuoco - Flammability - Classement au feu - Feuersicherung**

può superare - can meet - peut surmonter - überwinden

UNI 9174 - 8456 Class C1  
UNI 9175 Class 1 IM  
DIN 4102 Class B1  
NF 92501-7 Class M1  
NF D 60013 Class AM18  
EN 1021-1 & 2  
BS Crib 5  
BS 7176 Class Medium Hazard  
EN 13773 Class 1  
OENORM 3800-1 Class B1,Q1,TR1  
California TB117  
USA NFPA 701  
USA NFPA 260  
IMO Part 8 Upholstery

Altri test fuoco possono essere superati, il superamento di alcuni test fuoco può dipendere dalla schiuma utilizzata

Will also pass other flammability standards. Flame retardant performance is dependent upon the foam used

Autres tests feu peuvent être passés. La performance au feu dépend de la mousse utilisée

Wird auch andere Brandschutzstandards erfüllen. Die flammhemmende Leistung ist anhängig von dem verwendeten Schaum

**Manutenzione e lavaggio - Cleaning and washing - Nettoyage et lavage - Reinigung und waschen**

