Biella Qualità Totale s.r.l.

n° 0143

To
FIDIVI Tessitura Vergnano spa
Reg. Masio, 19 bis
10046 POIRINO (TO)

Biella, 03/11/06

Attn of SIG.PRESTIGIACOMO

TEST REPORT

Test #	date	Pag.
8872	31/10/2006	1/1

Sample identification	Date of arrival	Sample id #	Sample reference
	18/10/2006	06.00293.07	

Article : KING FLEX
Variant :
Colour :
Piece # :
Supplier : Medesimo

Test: COLOUR FASTNESS TO LIGHT

Form and terms
Apparatus : XENOTEST
Test method : UNI EN ISO 105 B02/2004 Met.1 : Solidità del colore alla luce artificiale - lampada ad arco allo xeno (color fastness to light).
Temperature : 45 °C
Humidity : 50 %
Assessment : Blu standard scale

Test results	Test start	Test end	Notes
	19/10/2006	31/10/2006	

RESULT : 6

The result complies with the Norm UNI EN 14465/05 class A

Measure uncertainty

Signatures
The operator: (p.i. Federica Bozzo)
The laboratory responsible: (dr. Paolo Furno Marchese)

Tests have been conducted in normal environment (20 ± 2 °C; 65 ± 4% RH) and after 24 hours of specimen acclimatizing.
Test results are referred only to the tested sample
Remaining cloth will be kept for 40 days, except different customer's request
Total or partial reproduction of this report must be autorized with letter by BQT Laboratory

Mod. 01 Rev. 11