



LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N. 1555	date 27/01/2022	Pag. 1/1				
<u>Sample identification</u>		Date of arrival 24/01/2022	Sample id 22.00028.10		Sample reference				
Article : NAUTILUS									
<table border="1"> <thead> <tr> <th>Test</th> <th>COLOUR FASTNESS TO WET RUBBING</th> </tr> </thead> <tbody> <tr> <td colspan="2"> Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER N.of rubs : 10 Material : Wet cotton cloths Load : 9 N Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4% Environment of testing : 20+/-2°C and R.H.65+/-4% </td> </tr> </tbody> </table>						Test	COLOUR FASTNESS TO WET RUBBING	Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER N.of rubs : 10 Material : Wet cotton cloths Load : 9 N Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4% Environment of testing : 20+/-2°C and R.H.65+/-4%	
Test	COLOUR FASTNESS TO WET RUBBING								
Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER N.of rubs : 10 Material : Wet cotton cloths Load : 9 N Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4% Environment of testing : 20+/-2°C and R.H.65+/-4%									
<u>Test results</u>		Test start 27/01/2022	Test end 27/01/2022	Notes					
Staining Longitudinal : 4/5 index Staining Transversal : 4/5 index									
Measure uncertainty extended:				Signatures The Textile Laboratory Manager (Dr. Jessica Fabbro)					
				CEO (Eng. Alberto Canova)					

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.

END OF TEST REPORT

Biella Qualità Totale srl

Via F. Piacenza, 26/a - 13900 BIELLA (BI) - Tel. +39 015 8497586 Fax +39 015 8497931 - P. Iva 01735920025
CCIAA Biella n. 160437 - Reg. Società n. 13770 Tribunale di Biella - Capitale sociale € 286.000,00 int. vers

Mod. 01 Rev. 20



LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N. 1556	date 27/01/2022	Pag. 1/1																																																						
<u>Sample identification</u>		Date of arrival 24/01/2022	Sample id 22.00028.10		Sample reference																																																						
Article : NAUTILUS																																																											
<table border="1"> <thead> <tr> <th>Test</th> <th colspan="5">COLOUR FASTNESS TO DRY RUBBING</th> </tr> </thead> <tbody> <tr> <td colspan="6">Form and terms</td> </tr> <tr> <td>Test method</td> <td colspan="5">: UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing</td> </tr> <tr> <td>Apparatus</td> <td colspan="5">: CROCKMETER</td> </tr> <tr> <td>N.of rubs</td> <td colspan="5">: 10</td> </tr> <tr> <td>Material</td> <td colspan="5">: Dry cotton cloths</td> </tr> <tr> <td>Load</td> <td colspan="5">: 9 N</td> </tr> <tr> <td>Conditioning</td> <td colspan="5">: Minimum 4 hours at 20+/-2°C and R.H.65+/-4%</td> </tr> <tr> <td>Environment of testing</td> <td colspan="5">: 20+/-2°C and R.H.65+/-4%</td> </tr> </tbody> </table>						Test	COLOUR FASTNESS TO DRY RUBBING					Form and terms						Test method	: UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing					Apparatus	: CROCKMETER					N.of rubs	: 10					Material	: Dry cotton cloths					Load	: 9 N					Conditioning	: Minimum 4 hours at 20+/-2°C and R.H.65+/-4%					Environment of testing	: 20+/-2°C and R.H.65+/-4%				
Test	COLOUR FASTNESS TO DRY RUBBING																																																										
Form and terms																																																											
Test method	: UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing																																																										
Apparatus	: CROCKMETER																																																										
N.of rubs	: 10																																																										
Material	: Dry cotton cloths																																																										
Load	: 9 N																																																										
Conditioning	: Minimum 4 hours at 20+/-2°C and R.H.65+/-4%																																																										
Environment of testing	: 20+/-2°C and R.H.65+/-4%																																																										
<u>Test results</u>		Test start 27/01/2022	Test end 27/01/2022	Notes																																																							
Staining Longitudinal :4/5 index		Staining Transversal :4/5 index																																																									
Measure uncertainty extended:				Signatures The Textile Laboratory Manager (Dr. Jessica Fabbro)																																																							
				CEO (Eng. Alberto Canova)																																																							

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.

END OF TEST REPORT

Biella Qualità Totale srl

Via F. Piaccenza, 26/a - 13900 BIELLA (BI) - Tel. +39 015 8497586 Fax +39 015 8497931 - P. Iva 01735920025
CCIAA Biella n. 160437 - Reg. Società n. 13770 Tribunale di Biella - Capitale sociale € 286.000,00 int. vers

Mod. 01 Rev. 20