





LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test report N° S.8418	Test N° 24.10017	date 21-05-2024	Pag. 1/1
<u>Sample identification</u>	Date of arrival 17-05-2024	Sample id 24.00213.06	Sample reference			
Article : ONE						
Test	COLOUR FASTNESS TO WET RUBBING					
<p>Form and terms</p> <p>Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing</p> <p>Apparatus : CROCKMETER</p> <p>N.of rubs : 10</p> <p>Material : Wet cotton cloths</p> <p>Load : 9 N</p> <p>Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4%</p> <p>Environment of testing : 20+/-2°C and R.H.65+/-4%</p> <p>Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain</p>						
<u>Test results</u>	Test start 21-05-2024	Test end 21-05-2024	Notes			
<p>Staining Longitudinal :4/5 index</p> <p>Staining Transversal :4/5 index</p>						
Measure uncertainty extended:			<p>Signatures</p> <div style="display: flex; justify-content: space-between;"> <div style="text-align: center;"> <p>The Textile Laboratory Manager</p>  <p>(Dr. Jessica Fabbro)</p> </div> <div style="text-align: center;"> <p>CEO</p>  <p>(Eng. Alberto Canova)</p> </div> </div>			



Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its integrity, unless approved in writing by BQT laboratory.



LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test report N° S.8417	Test N° 24.10016	date 21-05-2024	Pag. 1/1
<u>Sample identification</u>	Date of arrival 17-05-2024	Sample id 24.00213.06	Sample reference			
Article : ONE						
Test	COLOUR FASTNESS TO DRY RUBBING					
Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER N.of rubs : 10 Material : Dry cotton cloths Load : 9 N Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4% Environment of testing : 20+/-2°C and R.H.65+/-4% Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain						
<u>Test results</u>	Test start 21-05-2024	Test end 21-05-2024	Notes			
Staining Longitudinal :4/5 index Staining Transversal :4/5 index						
Measure uncertainty extended:			Signatures <div style="display: flex; justify-content: space-between;"> <div style="text-align: center;"> The Textile Laboratory Manager  (Dr. Jessica Fabbro) </div> <div style="text-align: center;"> CEO  (Eng. Alberto Canova) </div> </div>			

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its intirety, unless approved in writing by BQT laboratory.