

 TESSITURA VERGNANO	CARATTERISTICHE PRINCIPALI - PRINCIPAL CHARACTERISTICS CARACTERISTIQUES PRINCIPALES - HAUPT EIGENSCHAFTEN	Date 04/04/2022 Edition 00
--	--	-------------------------------

Caratteristica Characteristic Caractéristique Charakterdarsteller	Norma Norm Norme Norm	Tolleranza Tolerance Tolérance Toleranz	Dichiarato Declared Déclaré Deklariert
Peso (g/ml) – Weight (g/lm) Poids (g/ml) - Gewicht (g/lm)	EN 12127	± 5 %	420
Peso (g/m²) - Weight (g/m²) Poids (g/m²) - Gewicht (g/m²)	EN 12127	± 5 %	310
Altezza (cm) - Width (cm) Largeur (cm) - Breite (cm)	-----	± 2 %	135
Resistenza all'abrasione (cicli) Abrasion resistance (rubs) Résistance à l'abrasion (tours) Scheuerfestigkeit (Scheuertouren)	ISO 12947-2 (Martindale)	± 10 %	> 200.000
Solidità del colore alla luce (scala dei blu) Light fastness (blue scale) Solidité à la lumière (échelle des bleu) Lichtechtheit (Blaumaßstabe)	ISO 105-B02 (Xenotest)	da 5 a 8	6
Solidità del colore allo sfregamento (scala dei grigi) Fastness to rubbing (grey scale) Solidité au frottement (échelle des gris) Reibechtheit (Graumaßstabe)	ISO 105-X12 (Crockmeter)	da 4 a 5	4/5
Pilling (2000 cicli) - Pilling (2000 rubs) Pilling (2000 tours) - Pilling (2000 scheuertouren)	ISO 12945-2	da 4 a 5	5
Composizione Composition Composition Zusammensetzung	100% POLIAMMIDE RICICLATA ECONYL® 100% RECYCLED POLYAMIDE ECONYL® 100% POLYAMIDE RECYCLÉ ECONYL® 100% RECYCELTES POLYAMIDE ECONYL®		
Leggere differenze di colore tra un lotto e l'altro sono da considerarsi normali Slight colour differences between one lot and another have to be considered within commercial tolerance Légères différences de couleur entre un lot et l'autre doivent être considérés comme étant normales Leichte Farbunterschiede sind zwischen zwei Partien als normal zu betrachten			
Reazione al fuoco – Flammability - Classement au feu – Feuersicherung			
Can meet UNI 9175 Class 1 IM EN 1021-1 & 2 BS 7176 Class Low Hazard California TB 117-2013	Altri test fuoco possono essere superati, il superamento di alcuni test fuoco può dipendere dalla schiuma utilizzata Will also pass other flammability standards. Flame retardant performance is dependent upon the foam used Autres tests feu peuvent être passés. La performance au feu dépend de la mousse utilisée Wird auch andere Brandschutzstandards erfüllen. Die flammhemmende Leistung ist anhängig von dem verwendeten Schaum		
Manutenzione e lavaggio – Cleaning and washing – Nettoyage et lavage – Reinigung und waschen			
30 P			
ECONYL® OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 073313-0 CENTROCOT Notest for harmful substances. www.oeko-tex.com/standard100 Global Recycled Standard GRS Certified by ICEA [GRS 2020-138] GUARANTEE 5 YEARS			

PANAREA