



LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N. 2185	date 04/02/2022	Pag. 1/1
<u>Sample identification</u>		Date of arrival 24/01/2022	Sample id 22.00028.12		Sample reference
Article : PANAREA					
Test		COLOUR FASTNESS TO LIGHT			
Form and terms Test method : UNI EN ISO 105-B02:2014 Method 1 Textiles. Tests for colour fastness. Colour fastness to artificial light: Xenon arc fading lamp Apparatus : XENOTEST Q-SUN Xe2 Assessment : Blue scale Condition : Normal Type of exposition : Continuous Humidity : 40%					
<u>Test results</u>		Test start 24/01/2022	Test end 04/02/2022	Notes	
Fastness index : 6					
Measure uncertainty extended:		Signatures		The Textile Laboratory Manager On behalf of the Technical Manager (Dr. Jessica Fabbro) (Dr. Sebastiano Zanol)	

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.

END OF TEST REPORT

Biella Qualità Totale srl

Via F. Piacenza, 26/a - 13900 BIELLA (BI) - Tel. +39 015 8497586 Fax +39 015 8497931 - P. Iva 01735920025
CCIAA Biella n. 160437 - Reg. Società n. 13770 Tribunale di Biella - Capitale sociale € 286.000,00 int. vers

Mod. 01 Rev. 20