




LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N. 2502	date 10/02/2022	Pag. 1/1
<u>Sample identification</u>		Date of arrival 24/01/2022	Sample id 22.00028.12		Sample reference
Article : PANAREA					
Test start 03/02/2022	Test end 10/02/2022	ABRASION			
Test method : UNI EN ISO 12947-1:2000+EC 1-2010+UNI EN ISO 12947-2:2017 Textiles. Determination of the abrasion resistance of fabrics by the Martindale method. Determination of specimen breakdown Apparatus : MARTINDALE Material : Standard Abradent Fabric SM 25 Load : 12Kpa (nominal pressure) Felt : Woven felt Pilling : The possible pilling created during the test is cut RESULTS Breaking point: > 200000 revs Sample 1: > 200000 revs Sample 2: > 200000 revs Sample 3: > 200000 revs					
Notes		Signatures The Textile Laboratory Manager  (Dr. Jessica Fabbro)			
		CEO  (Eng. Alberto Canova)			

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT

END OF TEST REPORT

Biella Qualità Totale srl

Via F. Piacenza, 26/a - 13900 BIELLA (BI) - Tel. +39 015 8497586 Fax +39 015 8497931 - P. Iva 01735920025
CCIAA Biella n. 160437 - Reg. Società n. 13770 Tribunale di Biella - Capitale sociale € 286.000,00 int. vers

Mod. 01 Rev. 20