



COMPOSIZIONE 100% Poliestere Trevira CS® ECO Le proprietà ignifughe sono intrinseche nella fibra.	COMPOSITION 100% Polyester Trevira CS® ECO The flame-retardant properties are inherent to the fiber.	COMPOSITION 100% Polyester Trevira CS® ECO Les propriétés ignifuges sont intrinsèques à la fibre.	ZUSAMMENSETZUNG 100% Polyester Trevira CS® ECO Die flammhemmenden Eigenschaften sind intrinsisch in Faser.
PESO 450 ± 5% g/ml 320 ± 5% g/m²	WEIGHT 450 ± 5% g/lm 320 ± 5% g/m²	POIDS 450 ± 5% g/ml 320 ± 5% g/m²	GEWICHT 450 ± 5% g/lml 320 ± 5% g/m²
ALTEZZA 140 ± 2% cm	WIDTH 140 ± 2% cm	LARGEUR 140 ± 2% cm	BREITE 140 ± 2% cm
RESISTENZA ALL'ABRASIONE (Martindale) EN ISO 12947-2 100.000 ± 10% cicli	ABRASION RESISTANCE (Martindale) EN ISO 12947-2 100.000 ± 10% rubs	RÉSISTANCE À L'ABRASION (Martindale) EN ISO 12947-2 100.000 ± 10% tours	SCHEUERFESTIGKEIT (Martindale) EN ISO 12947-2 100.000 ± 10% Scheuertouren
PILLING EN ISO 12945-2 5 (foto standard) Tolleranza: da 4 a 5	PILLING EN ISO 12945-2 5 (standard pictures) Tolerance: from 4 to 5	PILLING EN ISO 12945-2 5 (photos standard) Tolérance: de 4 à 5	PILLING EN ISO 12945-2 5 (standard Bilder) Toleranz: von 4 bis 5
SOLIDITÀ ALLA LUCE EN ISO 105-B02 6 (scala dei blu) Tolleranza: da 5 a 8	LIGHT FASTNESS EN ISO 105-B02 6 (blue scale) Tolerance: from 5 to 8	SOLIDITÉ À LA LUMIÈRE EN ISO 105-B02 6 (échelle des bleus) Tolérance: de 5 à 8	LICHTTECHTHEIT EN ISO 105-B02 6 (Blaumaßstabe) Toleranz: von 5 bis 8
SOLIDITÀ ALLO SFREGAMENTO EN ISO 105-X12 4/5 (scala dei grigi) Tolleranza: da 4 a 5	FASTNESS TO RUBBING EN ISO 105-X12 4/5 (grey scale) Tolerance from 4 to 5	SOLIDITÉ AU FROTTEMENT EN ISO 105-X12 4/5 (échelle des gris) Tolérance: de 4 à 5	REIBECHTHEIT EN ISO 105-X12 4/5 (Graumaßstabe) Toleranz: von 4 bis 5
REAZIONI AL FUOCO EN 1021/1-2 BS 5852 CRIB 5 BS 7176 Medium Hazard NF P 92 501-7 M1 NF D 60013 AM 18 DIN 4102 Class B1 UNI 9174 Classe 1 UNI 9175 Classe 1IM CAL TB 117:2013 IMO Part 8 Upholstery	FLAMMABILITY EN 1021/1-2 BS 5852 CRIB 5 BS 7176 Medium Hazard NF P 92 501-7 M1 NF D 60013 AM 18 DIN 4102 Class B1 UNI 9174 Class 1 UNI 9175 Class 1IM CAL TB 117:2013 IMO Part 8 Upholstery	CLASSEMENT AU FEU EN 1021/1-2 BS 5852 CRIB 5 BS 7176 Medium Hazard NF P 92 501-7 M1 NF D 60013 AM 18 DIN 4102 Class B1 UNI 9174 Class 1 UNI 9175 Class 1IM CAL TB 117:2013 IMO Part 8 Upholstery	FEUERSICHERUNG EN 1021/1-2 BS 5852 CRIB 5 BS 7176 Medium Hazard NF P 92 501-7 M1 NF D 60013 AM 18 DIN 4102 Class B1 UNI 9174 Class 1 UNI 9175 Class 1IM CAL TB 117:2013 IMO Part 8 Upholstery
Il grado di resistenza al fuoco dipende dal tipo di schiuma usato	Flame retardant performance is dependent upon the foam used	Le degré de résistance au feu dépend du type de mousse utilisé	Schwerentflammbarkeit hängt von verwendetem schaum ab
COLORE Leggere differenze di colore tra una partita e l'altra sono da considerarsi normali	COLOUR Slight color differences between one lot and another must be considered within commercial tolerance	COLORIS Les légères différences de couleur entre un lot et l'autre doivent être considérées comme étant normales	FARBABWEICHUNGEN Leichte Farbunterschiede sind zwischen zwei Partien als normal zu betrachten
MANUTENZIONE E LAVAGGIO 	CLEANING AND WASHING 	NETTOYAGE ET LAVAGE 	REINIGUNG UND WASCHEN
Fare sempre riferimento al sito web per la versione più aggiornata della scheda tecnica	Always refer to the website for the most up-to-date version of the data sheet	Toujours se référer au site web pour obtenir la version la plus à jour de la fiche technique	Auf der Website finden Sie immer die aktuellste Version des Datenblattes

ED. 01



FIDIVI TESSITURA VERGNANO S.p.A.
Regione Masio 19 bis 10046 Poirino (TO) ITALY
tel. +39 0119430662 fax +39 0119430478
www.fidivi.com info@fidivi.com

