





LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N. 17101	date 13/10/2021	Pag. 1/1
<u>Sample identification</u>	Date of arrival 12/10/2021	Sample id 21.00465.06	Sample reference		
Article : SMART					
Test	COLOUR FASTNESS TO WET RUBBING				
Form and terms					
Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing					
Apparatus : CROCKMETER					
N.of rubs : 10					
Material : Wet cotton cloths					
Load : 9 N					
Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4%					
Environment of testing : 20+/-2°C and R.H.65+/-4%					
<u>Test results</u>	Test start 13/10/2021	Test end 13/10/2021	Notes		
Staining Longitudinal :4/5 index					
Staining Transversal :4/5 index					
Measure uncertainty extended:			Signatures		
			<div style="display: flex; justify-content: space-around;"> <div style="text-align: center;"> <p>The operator</p>  <p>(p.i. Federica Bozzo)</p> </div> <div style="text-align: center;"> <p>The Laboratory Director</p>  <p>(Ing. Alberto Canova)</p> </div> </div>		

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.

END OF TEST REPORT



LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa
Regione Masio, 19 bis
10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N. 17102	date 13/10/2021	Pag. 1/1
<u>Sample identification</u>	Date of arrival 12/10/2021	Sample id 21.00465.06	Sample reference		
Article : SMART					
Test	COLOUR FASTNESS TO DRY RUBBING				
Form and terms					
Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing					
Apparatus : CROCKMETER					
N.of rubs : 10					
Material : Dry cotton cloths					
Load : 9 N					
Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4%					
Environment of testing : 20+/-2°C and R.H.65+/-4%					
<u>Test results</u>	Test start 13/10/2021	Test end 13/10/2021	Notes		
Staining Longitudinal	:4/5	index			
Staining Transversal	:4/5	index			
Measure uncertainty extended:			Signatures		
			The operator (p.i. Federica Bozzo)		The Laboratory Director (Ing. Alberto Canova)

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.

END OF TEST REPORT

Biella Qualità Totale srl