





FIDIVI Tessitura Vergnano spa Regione Masio, 19 bis 10046 POIRINO (TO)

				At	tn of Sig. M. Full	in		
TEST REPORT					Test N. 13633	date 20/09/2022	Pag. 1/1	
Sample identification	Sample identification Date of arrival Sample id 22.00343.03				e reference			114.00
Article : SPA	ZIO							
				<u> </u>				
Test	COLOUR FASTNESS TO DRY RUBBING							
Form and terms Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER N.of rubs : 10 Material : Dry cotton cloths Load : 9 N Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4% Environment of testing : 20+/-2°C and R.H.65+/-4%								
Test results		Test start 20/09/2022	Test end 20/09/		Notes			

<u>Test results</u>	Test start 20/09/2022	Test end 20/09/2022	Notes	
0 0	:4/5 index :4/5 index			
Measure uncertainty extended:			Signatures The Textile Laboratory Manager (Dr. Jessica Fabbro)	CEO (Eng.Alberto Canova)

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsability. This test report can't be reproduced, except in its intirety, unless approved in writing by BQT laboratory.







FIDIVI Tessitura Vergnano spa Regione Masio, 19 bis 10046 POIRINO (TO)

million.	LAD 14 0143 E					
			Attn of Sig. M	. Fullin		
	TEST RE	EPORT		Test N. 13634	date 20/09/2022	Pag. 1/1
Sample identification	Date of arrival 19/09/2022	Sample id 22.00343.03	Sample reference			
Article : SPAZ	IO					
		N.				
Test		COLOUR FASTNESS TO WET RUBBING				
Form and terms Test method Apparatus N.of rubs Material Load Conditioning Environment of testing	: CROCKMETER : 10 : Wet cotton cloths : 9 N : Minimum 4 hours	s at 20+/-2°C and	es. Tests for colour fast	tness. Colour fastnes	s to rubbing	
Test results	Test start 20/09/2	Test end 20/09/2	Notes 2022			
Staining Longitudinal	:4/5 ir	ndex				

<u>Test results</u>	Test start 20/09/2022	Test end 20/09/2022	Notes	
Staining Longitudinal Staining Transversal	:4/5 index :4/5 index			
Measure uncertainty extended:			Signatures The Textile Laboratory, Manager (Dr. Jessica Fabbro)	CEO (Eng. Alberto Canova)

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsability. This test report can't be reproduced, except in its intirety, unless approved in writing by BQT laboratory.