



LAB N° 0143 L

To FIDIVI Tessitura Vergnano spa  
 Regione Masio, 19 bis  
 10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N. 1562	date 27/01/2022	Pag. 1/1
<u>Sample identification</u>	Date of arrival 24/01/2022	Sample id 22.00028.11	Sample reference		
Article : STROMBOLI					
Test	COLOUR FASTNESS TO WET RUBBING				
Form and terms					
Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing					
Apparatus : CROCKMETER					
N.of rubs : 10					
Material : Wet cotton cloths					
Load : 9 N					
Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4%					
Environment of testing : 20+/-2°C and R.H.65+/-4%					
<u>Test results</u>	Test start 27/01/2022	Test end 27/01/2022	Notes		
Staining Longitudinal	:4/5	index			
Staining Transversal	:4/5	index			
Measure uncertainty extended:			Signatures		
			The Textile Laboratory Manager  (Dr. Jessica Fabbro)		CEO  (Eng. Alberto Canova)
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.</small>					


END OF TEST REPORT



LAB N° 0143 L

 To FIDIVI Tessitura Vergnano spa  
 Regione Masio, 19 bis  
 10046 POIRINO (TO)

Attn of Sig. M. Fullin

TEST REPORT			Test N. 1561	date 27/01/2022	Pag. 1/1
<u>Sample identification</u>	Date of arrival 24/01/2022	Sample id 22.00028.11	Sample reference		
Article : STROMBOLI					
Test	COLOUR FASTNESS TO DRY RUBBING				
Form and terms	Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing Apparatus : CROCKMETER N.of rubs : 10 Material : Dry cotton cloths Load : 9 N Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4% Environment of testing : 20+/-2°C and R.H.65+/-4%				
<u>Test results</u>	Test start 27/01/2022	Test end 27/01/2022	Notes		
Staining Longitudinal	:4/5	index			
Staining Transversal	:4/5	index			
Measure uncertainty extended:			Signatures The Textile Laboratory Manager  (Dr. Jessica Fabbro)		
			CEO  (Eng. Alberto Canova)		

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.

END OF TEST REPORT