

TEST REPORT N° 18/24035

page 1 out of 2

Mod.018 Rev. 2 del 12.10.2015

WEB Request Number	
Receipt Number	18/23489
Receipt date	24/05/18
Test beginning date	25/05/18
Test end date	30/05/18
Document issued on	30/05/18

FIDIVI TESSITURA VERGNANO S.p.A.

Regione Masio, 19 bis
10046 POIRINO (TO)
Phone +39 (011) 9430662
Fax +39 (011) 9461820



SAMPLE IDENTIFICATION:

A TESSUTO ART. TERRA

THIS DOCUMENT CONTAINS THE FOLLOWING TESTS:

Code	Test	Test Method
CS0210	Colour fastness to artificial light - Xenon arc fading lamp	UNI EN ISO 105-B02:2014; ISO 105-B02:2014

Tests results refer only to tested samples submitted by the customer.
On each page there is the Institute dry stamp.
Tested samples are available for 3 months.

<p>The Analysts</p>  <p>Prof. Andrea Franchi</p>	<p>Technical Manager</p>  <p>Prof. Giuseppe Bartolini</p>
--	--

Private document. It is not allowed to publish and spread it without lab's written authorization.

TEST REPORT N° 18/24035

page 2 out of 2

Mod.018 Rev. 2 del 12.10.2015

Beginning of Test Report

CS0210 Colour fastness to artificial light - Xenon arc fading lamp

Test methods **UNI EN ISO 105-B02:2014; ISO 105-B02:2014**

Rev.1.0 -25/03/2016

Test environment Colour Fastness index (Blu Scale): 1 min - 8 max

Method 2

Testing equipment Xenotest Alpha / Xenotest 440 - Atlas

Testing date 30/05/2018

Test Results :

<i>Sample identification</i>	TESSUTO ART. TERRA
<i>Fastness index</i>	6

NB. The results reported in the tables above refer to a test analysis of the samples submitted.

End of Test Report.