



To FIDIVI Tessitura Vergnano spa
 Regione Masio, 19 bis
 10046 POIRINO (TO)



LAB N° 0143 L

Attn of Sig. M. Fullin

TEST REPORT			Test N. 5753	date 17/03/2021	Pag. 1/1
<u>Sample identification</u>		Date of arrival 04/03/2021	Sample id 21.00113.02	Sample reference	
Article : TERRA					
Test start 10/03/2021	Test end 17/03/2021	ABRASION			
<p>Test method : UNI EN ISO 12947-1:2000+EC 1-2010+UNI EN ISO 12947-2:2017 Textiles. Determination of the abrasion resistance of fabrics by the Martindale method. Determination of specimen breakdown Apparatus : MARTINDALE Material : Standard Abradent Fabric SM 25 Load : 12Kpa (nominal pressure) Felt : Woven felt Pilling : The possible pilling created during the test is cut Martindale : A3</p> <p>RESULTS Breaking point: > 150000</p> <p>Sample 1: > 150000 Sample 2: > 150000 Sample 3: > 150000</p>					
Notes		Signatures <div style="display: flex; justify-content: space-around;"> <div style="text-align: center;"> The operator  (p. i. Federica Bozzo) </div> <div style="text-align: center;"> The Laboratory Director  (Ing. Alberto Canova) </div> </div>			

Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.

END OF TEST REPORT

Biella Qualità Totale srl