



To FIDIVI Tessitura Vergnano spa
 Regione Masio, 19 bis
 10046 POIRINO (TO)



LAB N° 0143 L

Attn of Sig. M. Fullin

TEST REPORT			Test N. 8235	date 26/04/2021	Pag. 1/1
<u>Sample identification</u>	Date of arrival 22/04/2021	Sample id 21.00202.06	Sample reference		
Article : TIME					
Test	COLOUR FASTNESS TO WET RUBBING				
Form and terms					
Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing					
Apparatus : CROCKMETER					
N.of rubs : 10					
Material : Wet cotton cloths					
Load : 9 N					
Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4%					
Environment of testing : 20+/-2°C and R.H.65+/-4%					
<u>Test results</u>	Test start 26/04/2021	Test end 26/04/2021	Notes		
Staining Warp	:5	index			
Staining Weft	:5	index			
Measure uncertainty extended:			Signatures		
			The operator		The Laboratory Director
			 (p.i. Federica Bozzo)		 (Ing. Alberto Canova)
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.</small>					

END OF TEST REPORT

Biella Qualità Totale srl

Via F. Piacenza, 26/a - 13900 BIELLA (BI) - Tel. +39 015 8497586 Fax +39 015 8497931 - P. Iva 01735920025
 CCIAA Biella n. 160437 - Reg. Società n. 13770 Tribunale di Biella - Capitale sociale € 286.000,00 int. vers



Mod. 01 Rev. 19

To FIDIVI Tessitura Vergnano spa
 Regione Masio, 19 bis
 10046 POIRINO (TO)



LAB N° 0143 L

Attn of Sig. M. Fullin

TEST REPORT			Test N. 8236	date 26/04/2021	Pag. 1/1
<u>Sample identification</u>	Date of arrival 22/04/2021	Sample id 21.00202.06	Sample reference		
Article : TIME					
Test	COLOUR FASTNESS TO DRY RUBBING				
Form and terms					
Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing					
Apparatus : CROCKMETER					
N.of rubs : 10					
Material : Dry cotton cloths					
Load : 9 N					
Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4%					
Environment of testing : 20+/-2°C and R.H.65+/-4%					
<u>Test results</u>	Test start 26/04/2021	Test end 26/04/2021	Notes		
Staining Warp	:5	index			
Staining Weft	:5	index			
Measure uncertainty extended:			Signatures		
			The operator  (p.i. Federica Bozzo)		
			The Laboratory Director  (Ing. Alberto Canova)		
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Material sent to us for testing activities will not be kept for more than 40 days, unless otherwise requested by customer. Sample identification data are provided by customer and BQT declines all responsibility. Partial reproduction of this report must be authorized with a signed letter by BQT.</small>					

END OF TEST REPORT