

**TEST REPORT N° 17/01658**

**page 1 out of 2**

Mod.018 Rev. 2 del 12.10.2015

<b>WEB Request Number</b>	
<b>Receipt Number</b>	<b>17/564</b>
<b>Receipt date</b>	<b>10/01/17</b>
<b>Test beginning date</b>	<b>12/01/17</b>
<b>Test end date</b>	<b>20/01/17</b>
<b>Document issued on</b>	<b>20/01/17</b>

**FIDIVI TESSITURA VERGNANO S.p.A.**

**Regione Masio, 19 bis  
10046 POIRINO (TO)  
Phone +39 (011) 9430662  
Fax +39 (011) 9461820**



**SAMPLE IDENTIFICATION:**

**A TESSUTO ART. LANGHE**

**THIS DOCUMENT CONTAINS THE FOLLOWING TESTS:**

<b>Code</b>	<b>Test</b>	<b>Test Method</b>
CS0210	Colour fastness to artificial light - Xenon arc fading lamp	UNI EN ISO 105-B02:2014; ISO 105-B02:2014

Tests results refer only to tested samples.  
On each page there is the Institute dry stamp.  
Tested samples are available for 3 months.

<b>The Analysts</b>	<b>Technical Manager</b>
Prof. Analea Franchi - Prof. Paolo Borgioffi 	Prof. Giuseppe Bartolini 

Private document. It is not allowed to publish and spread it without lab's written authorization.

**TEST REPORT N° 17/01658**

**page 2 out of 2**

Mod.018 Rev. 2 del 12.10.2015

Beginning of Test Report

CS0210 Colour fastness to artificial light - Xenon arc fading lamp

*Test methods* **UNI EN ISO 105-B02:2014; ISO 105-B02:2014**

Rev.1.0 -25/03/2016

*Test environment* Colour Fastness index (Blu Scale): 1 min - 8 max

*Method* 2

*Testing equipment* Xenotest Alpha - Atlas

*Testing date* 20/01/2017

**Test Results :**

<i>Sample identification</i>	<b>TESSUTO ART. LANGHE</b>
<i>Fastness index</i>	<b>7</b>

*NB. The results reported in the tables above refer to a test analysis of the samples submitted.*

End of Test Report.