

**TEST REPORT N° 16/41978**

**page 1 out of 2**

Mod.018 Rev. 2 del 12.10.2015

<b>WEB Request Number</b>	
<b>Receipt Number</b>	<b>16/41173</b>
<b>Receipt date</b>	<b>06/12/16</b>
<b>Test beginning date</b>	<b>06/12/16</b>
<b>Test end date</b>	<b>09/12/16</b>
<b>Document issued on</b>	<b>15/12/16</b>

**FIDIVI TESSITURA VERGNANO S.p.A.**

**Regione Masio, 19 bis**  
**10046 POIRINO (TO)**  
**Phone +39 (011) 9430662**  
**Fax +39 (011) 9461820**



**SAMPLE IDENTIFICATION:**

**A TESSUTO ART. RIVA 100%TREVIRA CS**

**THIS DOCUMENT CONTAINS THE FOLLOWING TESTS:**

<b>Code</b>	<b>Test</b>	<b>Test Method</b>
CS0310	Color fastness to rubbing	UNI EN ISO 105-X12:2016

Tests results refer only to tested samples.  
On each page there is the Institute dry stamp.  
Tested samples are available for 3 months.

<b>The Analysts</b>	<b>Technical Manager</b>
Prof. Andrea Franchi - Prof. Paolo Borgiotti 	Prof. Giuseppe Bartolini 

Private document. It is not allowed to publish and spread it without lab's written authorization.

**TEST REPORT N° 16/41978**

**page 2 out of 2**

Mod.018 Rev. 2 del 12.10.2015

Beginning of Test Report

CS0310	Color fastness to rubbing
<i>Test methods</i>	<b>UNI EN ISO 105-X12:2016</b>

Rev.1.0 -25/03/2016

*Testing date* 09/12/2016

**Test Results :**

<i>Sample identification</i>	<b>TESSUTO ART. RIVA 100%TREVIRA CS</b>	
	<i>Staining index</i>	
	<i>Warp</i>	<i>Weft</i>
<i>Dry rubbing</i>	<b>4/5</b>	<b>4/5</b>
<i>Wet rubbing</i>	<b>5</b>	<b>5</b>

*Nota: for plain fabric, test is performed with circular finger; for raised fabric, test is performed with rectangular finger*

*NB. The results reported in the tables above refer to a test analysis of the samples submitted.*

End of Test Report.